



**NEWTC COMPOUND**  
**NA21**  
**Flexible PVC**

PROPERTIES	TYPICAL VALUES	TEST METHODS
SPECIFIC GRAVITY	1.27	ASTM D-792
HARDNESS (Shore A Durometer)	75	ASTM D-2240
TENSILE STRENGTH (psi)	2650	ASTM D-412
ELONGATION (%)	350	ASTM D-412
BRITTLENESS TEMPERATURE (°C.)	-26	ASTM D-746
TEMPERATURE RATING (°C.)	105	UL 1581
GLOSSY TEXTURE		

CONFIDENTIAL  
PROPERTY OF NEWTC

New England Wire Technologies Corporation Material Data Sheet	Typical Properties for <b>NA21</b>	Issue Date <b>9/4/2014</b>
The information contained in this data sheet is believed to be accurate and reliable but is furnished without guarantee, implied or expressed, on the part of New England Wire Technologies Corporation.		
This document and the information contained herein is considered NEWTC PROPRIETARY & CONFIDENTIAL.		