



SPECIFICATION:

- (1) ITEM NO. BS-IR
- (2) SNAP: WITH 6 PRONG SNAP
TERMINAL COPPER.
- (3) WIRE: UL1007 AWG#26 150m/m
BLACK & RED
- (4) MATERIAL: ABS MATERIAL CASING



COMFORTABLE ELECTRONIC CO., LTD.

NAME	RIGID BATTERY SNAP		
SCALE	2:1	APPD.	
UNIT	MM	CHKD	5/28/93
MAT'L	ABS	DWN.	
DATE	'93.FEB.4	DR NO	BSI2601

Test Report

No.: SZTYR040921237/LP

Date: SEP 16, 2004

Page 1 of 2

COMF ELECTRONIC FACTORY DONGGUAN
TANG WEI INDUSTRIAL AREA, SHI PAI,
DONGGUAN CITY, GUANGDONG PROVINCE, CHINA

Report on the submitted sample said to be BATTERY HOLDER WITH POLYPROPYLENE MATERIAL

SGS Job No. : 1610800
SGS Ref. No. : 2002354/EC
Sample Receiving Date : SEP 08, 2004
Testing Period : SEP 08, 2004 TO SEP 14, 2004

Test Requested : 1) To determine the Lead Content in the submitted sample.
2) To determine the Cadmium Content in the submitted sample.
3) To determine the Mercury Content in the submitted sample.
4) To determine the Hexavalent Chromium Content in the submitted sample.
5) Determination of PBBs (polybrominated biphenyls), PBDEs (Polybrominated diphenylethers) in the submitted sample.

Test Method : 1) With reference to EPA Method 3050B: 1996.
2) With reference to EN1122: 2001 Method B.
3) With reference to EPA Method 3052: 1996.
4) With reference to EPA Method 3060A: 1996.
Analysis was performed by Atomic Absorption Spectrometer (AAS) and Inductively Coupled Plasma Atomic Emission Spectrometer (ICP-AES).
5) With reference to SGS in-house method. Analysis was performed by GC/MS.

Test Results : Please refer to next page.

Signed for and on behalf of
SGS-CSTC Ltd.



This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.

SZL 273406

SGS-CSTC Standards Technical Services Co., Ltd. 2/F, 4/F, 5/F, Oastar Building, Zhongkang Road, Shangmeilin, Shenzhen China 518049 t (86-755)83114358 f (86-755)83106190 83118634 www.sgscstc.com
Shenzhen Branch-Toys Laboratory. 中国·深圳·上梅林中康路奥士达大厦2楼、4楼、5楼 邮编: 518049 t (86-755)83114358 f (86-755)83106190 83118634 e sgs_china@sgs.com

Member of SGS Group (Société Générale de Surveillance)

Test Report

No.: SZTYR040921237/LP

Date: SEP 16, 2004

Page 2 of 2

Test Results

Element	Black plastic parts
1) Lead (Pb)	3 ppm
2) Cadmium (Cd)	< 2 ppm
3) Mercury (Hg)	< 2 ppm
4) Hexavalent Chromium (Cr ⁶⁺)	< 2 ppm

Note : - < = Less than
 - ppm = mg/kg
 - Results shown are of the total weight of dry samples

5) Content of PBBs (polybrominated biphenyls); PBDEs (Polybrominated diphenylethers)

Flame Retardants	Black plastic parts	Detection Limit
Polybrominated Biphenyls (PBBs)	---	---
Monobromobiphenyl	N.D.	5 ppm
Dibromobiphenyl	N.D.	5 ppm
Tribromobiphenyl	N.D.	5 ppm
Tetrabromobiphenyl	N.D.	5 ppm
Pentabromobiphenyl	N.D.	5 ppm
Hexabromobiphenyl	N.D.	5 ppm
Heptabromobiphenyl	N.D.	5 ppm
Octabromobiphenyl	N.D.	5 ppm
Nonabromobiphenyl	N.D.	5 ppm
Decabromobiphenyl	N.D.	5 ppm
Polybrominated Diphenylether (PBDEs)	---	---
Monobromodiphenyl ether	N.D.	5 ppm
Dibromodiphenyl ether	N.D.	5 ppm
Tribromodiphenyl ether	N.D.	5 ppm
Tetrabromodiphenyl ether	N.D.	5 ppm
Pentabromodiphenyl ether	N.D.	5 ppm
Hexabromodiphenyl ether	N.D.	5 ppm
Heptabromodiphenyl ether	N.D.	5 ppm
Octabromodiphenyl ether	N.D.	5 ppm
Nonabromodiphenyl ether	N.D.	5 ppm
Decabromodiphenyl ether	N.D.	5 ppm

Note : - N.D. = Not Detected
 - Not detected is lower than detection limit value.
 - The test of 5) was conducted by SGS HK LTD.

*** End of Report ***

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.

SZL 273405