

THE PROPERTIES OF ALTUGLAS

MAIN CHARACTERISTICS

INDICATIVE VALUES ~

	TEST METHOD			UNITS	ALTUGLAS CN Thick Value mm		ALTUGLAS EX Thick Value mm	
	ISO	NF	Others					
GENERAL PROPERTIES								
Water absorbtion, 24 hrs.	R 62	T 51002	DIN 53495	%	4	0.30	4	0.30
Water absorbtion, 8 days	R 62	T 51002	DIN 53495	%	4	0.50	4	0.50
Water absorbtion, max. (total immersion, 1200 hrs.)			Interne	%	3	1.75	3	1.75
Density	R 1183	T 51063	DIN 53479			1.19		1.19
MECHANICAL PROPERTIES								
Poisson ratio to 20°C						0.39		0.39
Tensile strength to 23°C	R 527	T 51034	DIN 53455					
Stress at break				MPa	4	76	4	74
Modulus of elasticity				MPa	4	3300	4	3300
Elongation at break				%	4	6	4	5
Tensile strenght to - 20°C	R 527	T 31034	DIN 53455					
Stress at break				MPa	4	102		
Elongation at break				%	4	5		
Tensile strength to 80°C	R 527	t 51034	DIN 53455					
Stress at break				MPa	4	24		
Elongation to break				%	4	22		
Flexural strength to 23°C	178	T 51001	DIN 53452					
Stress at break				MPa	4	140	4	120
Modulus of elasticity				MPa	4	3000	4	3000
Charpy impact strength (un-notched)	179/1D	T 51035	DIN 53453	Kj/m ²	4	12	4	10
Izod impact strength (notched)	R 180		ASTM D256A	Kj/m ²	4	1.4	4	1.3
Hardness, Rockwell Scale M	D 2039		ASTM D 785			95		90
Hardness, Shore Scale D	R 868	T 51109				60-70		80
Compressive strength	R 684	T 51101	DIN 53454	MPa	4	130	4	110
Shear strength - dynamic modulus			DIN 53445	MPa		1700		1700
OPTICAL PROPERTIES								
Light transmittance	T 51068	DIN 5036						
3 mm thick				%	3	> 92	3	> 92
5 mm thick				%	5	> 92	5	> 92
9 mm thick				%			8	> 92
10 mm thick				%	10	> 92		
Refractive index	T 51064	DIN 53491				1.492		1.492

~ NB. The standards quoted are not always strictly equivalent. The values quoted are the average of results obtained under laboratory conditions and are given as an indication to enable customers to make best use of our products.

MAIN CHARACTERISTICS

INDICATIVE VALUES ~

	TEST METHOD			UNITS	ALTUGLAS CN		ALTUGLAS EX	
	ISO	NF	Others		Thick mm	Value	Thick mm	Value
ELECTRICAL PROPERTIES								
Dielectric strength		C 26225	DIN 53481	KV/mm		20 to 25		20 to 25
Transverse resistivity		C 26215	DIN 53482	Ohm.cm		> 10 ¹⁵		> 10 ¹⁵
Dielectric constant		C 26230	DIN 53483					
to 50 Hz	1183					3.7		3.7
to 1 MHz						2.6		2.6
THERMAL PROPERTIES								
Coefficient of linear expansion	EN 2155-1	T 51251	DIN 52328	mm/m/°C		0.065		0.070
Thermal conductivity			DIN 52612	W/m/°C		0.17		0.19
Specific heat			ASTM C 351	J/g/°C		1.32		1.32
Insulation coefficient K			DIN 4701					
3 mm thick				W/m²/°C	3	5.3	3	5.3
5 mm thick				W/m²/°C	5	5.1	5	5.1
10 mm thick				W/m²/°C	10	4.5	10	4.5
Vicat softening point B 10/10, conditioned samples	R 306	T 51021	DIN 53460	°C		> 110		> 103
Heat distortion temperature under load, 1.8 N/mm², conditioned samples	R 75/A	T 51005	DIN 53461	°C		109		102
Max. continuous service temperature				°C		85		80
Forming oven temperature				°C		130-180		140-170
Max. heating temperature				°C		200		190
Max. linear shrinkage after heating, thickness ≥ 3 mm				%		2		3
Max. linear shrinkage after heating, thickness < 3 mm				%		2		6
Max. superficial temperature under infra-red				°C		230		210
Degradation onset temperature				°C		285		240
FLAMMABILITY								
Self-ignition temperature				°C		approx. 430		approx. 430
Flame resistance (Radiant heat source)		P 92501			3	M4		M4
Melt behaviour when burning		P 92505			3	non-drip		drips
Flame resistance			DIN 4102			B2		B2
Flame resistance			BS 476 Pt. 7			class 3		class 4
Flame resistance			UL 94			HB		HB
Limiting Oxygen Index		T 5107	ASTM 2863 77	%		18		18
Chlorine content				%		0		0
Nitrogen content				%		< 0.02		< 0.02

~ NB. The standards quoted are not always strictly equivalent. The values quoted are the average of results obtained under laboratory conditions and are given as an indication to enable customers to make best use of our products.