

PERSPEX® CAST

PERSPEX®
FROM LUCITE®

The information given in this report is confidential. Its reproduction in whole, in part or in summary form without our written consent in each instance is expressly forbidden. The information is given in good faith and is based on our general experience, but because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.

Perspex® from Lucite® Cast - Technical Data Sheet

Range

Perspex® from Lucite® Cast Sheet is available in clear, opal and many colours in a range of thicknesses, sizes and special grades. Details are available in the Perspex Product Range (PX TC 602); further sizes, thicknesses or variants may be available on enquiry.

Masking

Perspex® from Lucite® sheet is supplied with double-sided, non-thermoformable PE masking. The showface masking is printed with the Perspex® logo.

Table of Properties

Values quoted for the properties of Perspex® from Lucite® Cast sheet are the results of tests on representative samples and do not constitute specifications

Talk to us
Tel: +44 (0)1254 874000
info@lucitesolutions.com
www.lucitesolutions.com

LUCITE®
The source of inspiration

technical data sheet

Property	Test Method	Units	Values
General Properties			
Density	ISO 1183	g cm ⁻³	1.19
Rockwell Hardness	ISO 2039-2	M scale	102
Water Absorption	ISO 62	%	0.2
Flammability	BS 476 Part 7 DIN 4102 NFP 92-507 UL94 ISO 11925-2	Class - - - -	3 B2 M4 HB E
Optical Properties			
Light Transmission	ASTM D1003	% (3 mm)	> 92
Refractive Index	ISO 489 A		1.49
Thermal Properties			
Vicat Softening Point	ISO 306 A	°C	> 110
Coefficient of Thermal Expansion - Linear	ASTM D696	x 10 ⁻⁵ . K ⁻¹	7.7
Specific Heat	ASTM C351	cal/g °C	0.35
Thermal Conductivity Coefficient (K Value)		W m m ⁻² °C	0.189
Heat Transfer Coefficient (U Value)		W m ⁻² °C	
- 3 mm single pane			5.2
- 5 mm single pane			4.9
Mechanical Properties			
Tensile strength (5 mm/min)	ISO 527	MPa	75
Elongation at Break (5 mm/min)	ISO 527	%	4
Flexural Strength (2 mm/min)	ISO 178	MPa	116
Flexural Modulus (2 mm/min)	ISO 178	MPa	3210
Impact Strength – Charpy (unnotched)	ISO 179	kJ m ⁻²	12
Poisson's Ratio			0.38

technical data sheet

Property	Test Method	Units	Values
Sound Insulation Properties			
Sound Reduction Index		db	
- 3 mm single pane			18
- 6 mm single pane			22
- 2 x 3 mm panes (20 mm air gap)			25
- 2 x 6 mm panes (20 mm air gap)			31
Electrical Properties			
Surface Resistivity	IEC 93	$\Omega \cdot m^{-2}$	$> 10^{14}$
Electrical Strength	IEC 243	$kV \cdot mm^{-1}$	15
Arc Resistance	ASTM D495		No tracking
Dielectric Constant	ASTM D150		
- 60 cycles			4
- 10^3 cycles			3
- 10^6 cycles			3
Power Factor	ASTM D150		
- 60 cycles			0.06
- 10^3 cycles			0.04
- 10^6 cycles			0.02

Perspex® and Lucite® are registered trademarks of the Lucite International UK Limited (registered in England No 3830161) group of companies.